

Product Data Sheet

Witcogel® TCV 70 Telephone Cable Compound

Product Description

TCV 70 telephone cable compound fully complies with among others the requirements for petrolatum jelly as prescribed in the B.P.O. specification M 142 and also meets the requirements of the "Deutsche Bundespost". TCV 70 is suitable for cold-filling techniques

Physical Properties

Properties	Unit	Method	Specification	Typical
Viscosity at 100°C	mm ² /s	ASTM D 445	Min. 18	21
Colour		ASTM D 1500	Max. 5.0	4.0
Drop Melting Point	°C	ASTM D 127	--	78
Dropping Point, on a sample conditioned as for Cone Penetration (ASTM D 937)	°C	ASTM D 566 (DIN 51801 Bl. 1)	Min. 73	77
Cone Penetration at 25°C	0.1 mm	ASTM D 937	70-90	76
COC Flash Point	°C	ASTM D 92	Min. 230	280
Relative Permittivity at 20°C	50 Hz	ASTM D 150	Max. 2.3	2.24
Volume Resistivity at 100°C	Gohm.m	ASTM D 1169	Min. 20	200
Plasticity -10°C		IEC 811.5.6	pass	pass
Requirements Bundespost - VDE 0472/807/C Germany			pass	pass
Requirements M 142 (BPO)			pass	pass
Requirements RTT (Belgium)			pass	pass
Requirements FT NF C 93-526, Annex C			pass	pass

Revision date: December 1, 2010

The information presented herein is based on the best data available and is believed to be correct. However, nothing stated in this bulletin is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our product or products; nor shall anything contained herein be constructed to constitute a permission or recommendation to practice any invention covered by a patent owned by Sonneborn Refined Products B.V., any of its division, or by other, without a license from the owner of the patent