

## Product Data Sheet

### Witcogel<sup>®</sup> TCV 98 R Telephone Cable Compound

#### ▪ Product Description

TCV 98 R has been developed for applications in using liquid techniques. When applied at temperatures of min. 95°C, cable will pass drainage test at 80°C, depending among others on filling temperatures, conductor/cable diameter and other filling conditions.

#### ▪ Physical Properties

Properties	Unit	Method	Specification	Typical
Viscosity at 120°C	mm <sup>2</sup> /s	ASTM D 445	120-150	135
Colour		ASTM D 1500	Max. 2.0	1.0
Drop Point	°C	IP 31 *	90-105	100
Drop Melting Point	°C	ASTM D 127	95-105	104
Cone Penetration at 25°C	0.1 mm	ASTM D 937	30-50	45
COC Flash Point	°C	ASTM D 92	Min. 240	250
Dissipation Factor at 25°C	1 MHz	ASTM D 150	<0.0015	0.0010
Volume Resistivity at 100°C	Gohm.m	ASTM D 1169	Min. 1000	1500
Di-Electric Constant, 25°C 1MHz		ASTM D 150	Max. 2.3	2,21
Simulated Cable Flow Test				
24 hr at 65-80 °C		REA PE 39	pass	pass
PE Absorption, 1d/70°C, MDPE	%	FTZ 72 TV-1	max. 10	6
Acid Value	mgKOH/g	IEC 538 B Cl 7	max. 0.05	max. 0.05

\*) sample conditioned according to  
ASTM D 937

Revision date: December 1, 2010

The information presented herein is based on the best data available and is believed to be correct. However, nothing stated in this bulletin is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our product or products; nor shall anything contained herein be construed to constitute a permission or recommendation to practice any invention covered by a patent owned by Sonneborn Refined Products B.V., any of its division, or by other, without a license from the owner of the patent