

Amber Technical II

Technical Petroleum Jelly

▪ Physical Properties

Properties	Unit	Method	Specification	Typical
Drop melting point	°C	ASTM D 127	70-80	77
Cone penetration at 25°C	dmm	ASTM D 937	90-115	105
Congealing point	°C	ASTM D 938	62-72	67
Colour		ASTM D 1500		Yellow/brown

Revision date: December 1, 2010

The information presented herein is based on the best data available and is believed to be correct. However, nothing stated in this bulletin is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our product or products; nor shall anything contained herein be constructed to constitute a permission or recommendation to practice any invention covered by a patent owned by Sonneborn Refined Products B.V., any of its division, or by other, without a license from the owner of the patent