

Specifications for
FLOODING COMPOUND 701

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Melting Point, °F	ASTM D127	200 Min.
Viscosity @ 302°F, SUS	ASTM D2161	300/400
Color	ASTM D1500	2.5 Max.
Flash Point, °F	ASTM D92	470 Min.
Slump/Flow Test, 2 hrs @ 160°F	LATM 040	PASS
Volume Resistivity, OHM-cm	ASTM D257	1X10 ¹⁴ Min.
Dissipation Factor @ 1MHZ	ASTM D150	0.0010 Max.
Dielectric Constant	ASTM D150	2.3 Max.