

Specifications for
WITCOGEL® II LV 0.2% AO Cable Filler

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Melting Point, °F	ASTM D127	196 Min.
Viscosity @ 230°F, SUS	ASTM D2161	200/240
Color	ASTM D1500	2.0 Max.
Oil Bleed	LATM 095	NONE
Dissipation Factor @ 1MHz	ASTM D150	0.0010 Max.
Dielectric Constant	ASTM D150	2.25 Max.
Volume Resistivity, OHM-cm	ASTM D257	1x10 ¹³ Min.
Slump/Flow Test, 2 hrs @ 190°F	LATM 040	PASS
Oxidative Induction Time, Min. *	LATM 099	10 Min.