

Specifications for WITCOGEL® IV Cable Filler

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Melting Point, °F	ASTM D127	196 Min.
Viscosity @ 230°F, SUS	ASTM D445	145/190
Color	ASTM D1500	2.0 Max.
Oil Bleed	LATM 095	NONE
Slump/Flow Test, 2 hrs @ 190°F	LATM 040	PASS
Oxidative Induction Time, Min.	LATM 099	40 Min.
Dissipation Factor @ 1MHz	ASTM D150	0.0010 Max.
Dielectric Constant	ASTM D150	2.25 Max.
Volume Resistivity, OHM-cm	ASTM D257	1x10 ¹³ Min.
Oxidation Induction Time, min.	LATM 099	10 Min.
Viscosity @ 230°F, cPs	ASTM D3236	Report

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.