

Specifications for
WITSOL® 45 INK OIL

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
SPECIFIC GRAVITY @ 60°F/60°F	ASTM D4052	0.795/0.810
SAYBOLT VISC. @ 100°F, SUS	ASTM D2161	34.0/36.0
UV ABSORBANCE	21CFR 178.3620(b)	PASS
COLOR, SAYBOLT	ASTM D156	20 Min.
BREAKDOWN TIME, Minutes	LATM 017	40 Min.
FLASH POINT, COC, °F	ASTM D92	210 Min.
DISTILLATION, IBP, °F	ASTM D86	450 Min.
DISTILLATION, FBP, °F	ASTM D86	545 Max.

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.